



(a) 100 parts by weight of at least one of (a-1) a singly water insoluble, silanol group-bearing silicone resin having the following average compositional formula:



wherein R^1 is a monovalent hydrocarbon group having 1 to 10 carbon atoms, R^2 is a substituted monovalent hydrocarbon group having 1 to 10 carbon atoms, X is a monovalent hydrocarbon group having 1 to 6 carbon atoms, m, n, p and q are positive numbers satisfying $0.5 \leq m \leq 1.8$, $0 \leq n \leq 1.0$, $0 < p \leq 1.5$, $0 \leq q \leq 0.5$, $0.5 \leq m+n \leq 1.8$, $0 < p+q \leq 1.5$, and $0.5 < m+n+p+q < 3$, and (a-2) a radical polymerizable vinyl group-bearing alkoxysilane having the following general formula:



wherein R^3 is hydrogen or methyl, R^4 is a divalent hydrocarbon group of 1 to 10 carbon atoms which may be separated by an oxygen atom, -COO- group or the like, R^5 is a substituted or unsubstituted monovalent hydrocarbon group having 1 to 8 carbon atoms, X is as defined above, "a" is 0 or 1, and "b" is 0 or 1, and

(b) 100 to 100,000 parts by weight of a radical polymerizable vinyl monomer.

✓
Please add the following new claims:

3. (New) The ink jet printing paper of claim 1, wherein R¹ is selected from the group consisting of methyl, ethyl, propyl, isopropyl, butyl, t-butyl, hexyl, cyclohexyl, octyl, decyl and phenyl.

sub
B1
AD
4. (New) The ink jet printing paper of claim 1, wherein R² is selected from the group consisting of (1) halogen atoms, (2) alkenyl groups, (3) epoxy functional groups, (4) (meth)acrylic functional groups, (5) amino functional groups, (6) sulfurous functional groups, (7) (polyoxyalkylene) alkyl ether groups, (8) anionic groups, and (9) quaternary ammonium salt structure-containing groups.

5. (New) The ink jet printing paper of claim 1, wherein X is selected from the group consisting of methoxy, ethoxy, isopropoxy groups.

6. (New) The ink jet printing paper of claim 1, wherein m is from 0.6 to 1.5.

7. (New) The ink jet printing paper of claim 1, wherein p is from 0.05 to 0.8.

8. (New) The ink jet printing paper of claim 1, wherein p is from 0.2 to 0.7.

9. (New) The ink jet printing paper of claim 1, wherein R³ is a hydrocarbon group of 1 to 6 carbon atoms.

403
B1
A2
and

10. (New) The ink jet printing paper of claim 1, wherein b is selected from the group consisting of (b-1) alkyl (meth)acrylates in which the alkyl moiety has 1 to 18 carbon atoms; (b-2) vinyl monomers containing a carboxyl group or anhydride group thereof; (b-3) hydroxyl group-containing vinyl monomers; (b-4) amide group-containing vinyl monomers; (b-5) amino group-containing vinyl monomers; (b-6) alkoxy group-containing vinyl monomers; (b-7) glycidyl group-containing vinyl monomers; (b-8) vinyl ester monomers; (b-9) aromatic vinyl monomers; (b-10) vinyl cyanide monomers; (b-11) vinyl halide monomers; (b-12) vinyl monomers containing at least two radical polymerizable unsaturated groups in a molecule; (b-13) (poly)oxyethylene chain-containing vinyl monomers; and (b-14) diorganopolysiloxanes composed of 1 to 200 siloxane units and having a radical polymerizable functional group at one end. --